



SEALER

ConTec CS-620C

DESCRIPTION

ConTec CS-620C sealer is an concentrated aqueous fine particle dispersion of acrylic polymer. It is designed to give all concrete masonry units tough, water-resistant properties. ConTec CS-620C is proven effective on porous concrete masonry surfaces. It can be applied in the field or on the dry side of the production line. ConTec CS-620C can be tinted using approved pigments.

APPLICATION

Dilute before using. Stir well. Spray systems should be airless type. There is no need to over apply. Only one coat is required. Apply only when substrate and ambient temperatures are above 64 degrees F. Maintain temp for 3 hours or until completely dry.

PACKAGING

ConTec CS-620C is available in bulk quantities or packaged in 55 gallon (208 L) drums weighing 480 lbs (218 kg) and 265 gallon (1003 L) totes weighing 2400 lbs (1089 kg).

TYPICAL PROPERTIES

Specific Gravity at 77F..... 1.00 - 1.02
 Viscosity at 77F, cps 100 max
 Weight per gallon8.4 - 8.5
 % Volatile matter (NVM(1)) ~ 55
 VOCs (lbs/gallon)012 lb/gal or 2.9 lb/ton

FEATURES / BENEFITS

- Deep penetrating.
- Concentrate saves freight.
- Non yellowing.
- Fast Drying - Reduces Blocking.
- Improves durability and chemical resistance.
- Reduces efflorescence on concrete products.
- Extremely blush resistant.

HANDLING / STORAGE

ConTec CS-620C can be stored over a wide range of temperatures but should not be allowed to freeze. Should ConTec CS-620C freeze, it will not thaw to a usable product. Provide adequate ventilation with use. Store as concentrate in original sealer container until just before usage.

ADDITION RATES

Dilute to appropriate solids level before using. 20% final solids is common but solids from 10% to 33% can be used. Add potable water and mix well.

Application rates can vary, depending on surface, from 100 to 420 square feet per gallon. Optimum coverage rates vary with geographic area. Always consult your ICT technical representative for recommendations for your application.

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.

Innovative Concrete Technology, LLC

bestadmix.com

92 Thomas Rd •Port Murray NJ • 07865 • Ph. 908-453-2737 • Fax 908-453-3634