



92 THOMAS RD PORT MURRAY, NJ 07865

ConTec CS-605

Description

ConTec CS-605 sealer is a aqueous fine particle dispersion of acrylic polymer. It is designed to give all concrete masonry units tough, water-resistant properties. ConTec CS-605 is proven effective on porous concrete masonry surfaces. It can be applied in the field or on the dry side of the production line. ConTec CS-605 can be tinted using approved pigments.

Features/Benefits

- Deep penetrating.
- Non yellowing.
- Fast Drying - Reduces Blocking.
- Improves durability and chemical resistance.
- Reduces efflorescence on concrete products.
- Extremely blush resistant.

Packaging

ConTec CS-605 is available in bulk quantities or packaged in 55 gallon (208 L) drums weighing 480 lbs (218 kg) and 265 gallon (1,003 L) totes weighing 2,400 lbs (1,089 kg).

Application

Spry Systems should be airless type. There is no need to over apply. Only one coat is required. Apply only when substrate and ambient temperatures are above 64°F. Maintain temp for 3 hours or until completely dry.

Handling/Storage

ConTec CS-605 can be stored over a wide range of temperatures but should not be allowed to freeze. Should CS-605 freeze, it will not thaw to a usable product. Provide adequate ventilation with use.

Addition Rates

ConTec CS-605 application rates can vary, depending on surface from 100 to 420 sqft per gallon. Optimum coverage rates vary with geographic area. Always consult your ICT representative for recommendations for your application.

Typical Properties

Specific Gravity at 77°F	1.00 - 1.02
Viscosity at 77°F, cps	100 max
Weight per gallon	8.4 - 8.5
% Volatile matter (NVM(1)).....	~ 80
VOCs (lbs/gallon)	012 lb/gal or 2.9 lb/ton

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.