



INFO@BESTADMIX.COM



(908)453-2737

92 THOMAS RD PORT MURRAY, NJ 07865

ConTec EC-135

Description

ConTec EC-135 is a integral water repellent admixture used in low slump concrete units such as architectural block, paving stones, SRW units, or masonry mortar. When used properly this unique formulation chemical reacts with concrete to prevent water penetration and control efflorescence. ConTec EC-135 contains new and improved primary efflorescence control and enhances the color and appeal of all types of concrete products. When used in both mortar and masonry units EC-135 reduces water infiltration through masonry walls.

Features/Benefits

- Increases hydrophobic properties and lowers absorption rates.
- Impedes the formation of primary and secondary efflorescence.
- Increases product durability with its unique densifying properties.
- Aids color development and can shorten production cycles.
- Reduces mechanical abrasion in equipment.

Packaging

ConTec EC-135 is available in bulk quantities or packaged in drums or totes.

Application

ConTec EC-135 can be used in all types of manufactured concrete in which the reduction of efflorescence and water permeability is desirable.

Handling/Storage

ConTec EC-135 should be stored at temperatures above 40°F (4.5°C). Care should be taken to prevent this product from freezing. Should EC-135 become frozen the resulting material will be unusable.

Addition Rates

We recommend the following range of dosage: 8 to 16 US fl. OZ. Per 100 lbs of cement for concrete paving stones and concrete roof tile. For SRW units and other architectural block higher dosage rates may be recommended. These dosage rates are estimated, your actual rate should be determined by testing. We recommend consulting your ICT representative to help you determine the proper dosage rate and order of addition for your particular process. Order of addition procedures can vary per facility. Never mix EC-135 with other admixtures before application.

Typical Properties

Specific Gravity at 77°F	1.008
Viscosity at 77°F, cps	<200
Weight per gallon	8.4
% Volatile matter (NVM(1))	~ 60

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.