



ConTec CS670WS

SEALER

DESCRIPTION

ConTec CS-670 wet-side sealer is an aqueous fine particle dispersion of acrylic polymer. It is designed to give all concrete masonry units tough, water-resistant properties. ConTec CS-670 is proven effective on porous concrete masonry surfaces. It can be applied in the field or on the dry or wet side of the production line.

FEATURES / BENEFITS

- Deep penetrating.
- May be applied wet-side.
- Fast Drying - Reduces Blocking.
- Improves durability and chemical resistance.
- Reduces efflorescence on concrete products.
- Extremely blush resistant.

APPLICATION

Spray systems should be airless type. There is no need to over apply. Only one coat is required. Apply only when substrate and ambient temperatures are above 55 degrees F. Maintain temp for 3 hours or until dry.

HANDLING / STORAGE

ConTec CS-670 can be stored over a wide range of temperatures but should not be allowed to freeze. Should ConTec CS-670 freeze, it will not thaw to a usable product. Provide adequate ventilation with use.

PACKAGING

ConTec CS-670 is available in bulk quantities or packaged in 55 gallon (208 L) drums weighing 480 lbs (218 kg) and 275 gallon (1003 L) totes weighing 2400 lbs (1089 kg).

ADDITION RATES

For wet-side apply enough to satisfy surface demand. Application rates can vary, depending on surface, from 100 to 420 square feet per gallon. Optimum coverage rates vary per application and geographic area. Always consult your ICT technical representative for recommendations for your application.

TYPICAL PROPERTIES

Specific Gravity at 77F..... 1.04 - 1.05
 Viscosity at 77F, cps < 400
 Weight per gallon8.65 - 8.75

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.

Innovative Concrete Technology, LLC
 bestadmix.com

92 Thomas Rd • Port Murray NJ • 07865 • Ph. 908-453-2737 • Fax 908-453-3634