# ConTec SP-311

#### DESCRIPTION

**ConTec SP-311** dry-cast plasticizer combines a swipe texturizing agent, lubricant, and a hydration aid in a single formulation. This unique admixture increases production rates, improves green strength, and produces a moderate to high swipe surface texture on formed dry cast concrete surfaces.

#### APPLICATION

**ConTec SP-311** is recommended for use in concrete masonry products and other dry-cast concrete applications where a moderate to high swipe texture is desired.

### PACKAGING

**ConTec SP-311** is available in tote and drum quantities. An ICT representative will determine the proper dispensing system for your operation.

## **TYPICAL PROPERTIES**

Form	Amber/Brown Liquid
Viscosity at 77°F, cps	
Density (lb./gal.)	8.4



#### **FEATURES / BENEFITS**

- Enhances cement dispersion/hydration
- Reduces cycle time and mold wear
- Imparts a moderate-high swipe texture
- Increases cohesion and green strength
- Improves edge and corner definition

## HANDLING / STORAGE

Store **ConTec SP-311** at temperatures above  $35^{0}$ F (2<sup>o</sup>C) and prevent from freezing. Should **ConTec SP-311** freeze, thaw completely then use mechanical agitation to reconstitute.

## ADDITION RATES

**ConTec SP-311** has a recommended dosage range of 2 to 5oz/cwt (130-325mL/100kg) of cementitious materials. Add separately to the mix if other admixtures are also being used. Never mix **ConTec SP-311** with other admixtures before use. Please consult an ICT representative for further recommendations and guidelines.

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.

### Innovative Concrete Technology, LLC

bestadmix.com

92 Thomas Rd, Port Murray NJ 07865 • Ph. 908-453-2737 • Fax 908-453-3634